



Air Distribution Concepts

204 Hallberg St.
PO BOX 507
Delavan, WI.
53115

flowCon Fabric Air Diffusers

Polyester Physical Characteristics

Construction.....300 denier Coated Polyester
With EPA approved antimicrobial agent

Weight.....7 oz. per sq. yard

Flame Retardancy..... Cal. Fire Marshall, NFPA-701
CPAI-84, ASTM-84 Class A
ICCes Report (ESR-2646) AC-167

Product tested in accordance with the 25/50
flame spread / smoke developed requirements
of NFPA 90-A .

Melt Temperature.....350 degrees F.

Tongue Tear.....Warp 43 lb.
Weft 48 lb. ASTM D2261-96

Air Permeability.....@ 125 Pa 0 cfm /sq. ft.

These are typical property values and are intended as guides only