



FlowCon

Fabric Air Diffusers

1505 Racine St.
PO BOX 507
Delavan, WI.
53115

Polyester Physical Characteristics

Construction.....300 denier acrylic coated polyester

Weight.....7 oz. per sq. yard

Flame Retardancy..... Cal. Fire Marshall, NFPA-701
CPAI-84, ASTM-84 Class A
(building material)

Melt Temperature.....350 degrees F.

Tongue Tear.....Warp 43 lb.
Weft 48 lb. ASTM D2261-96

These are typical property values and are intended as guides only.