



flowCon

Fabric Air Diffusers

1505 Racine St.
PO BOX 507
Delavan, WI.
53115

Polyethylene Physical Characteristics

Construction.....10mil...Woven HDPE scrim

Weight.....6 oz. per sq. yard

Flame Retardancy.....CAN/ULC s-109
Cal. Fire Marshall, NFPA-701
CPAI-84, Boston Fire Marshall

Melt Temperature.....180 degrees F.

Tongue Tear.....Warp 56 lb. 248 N
Weft 60 lb. 267N, ASTM D2261-96

These are typical property values and are intended as guides only.