



Polyester Physical Characteristics

Construction.....300 denier Coated Polyester
With EPA approved antimicrobial agent

Weight.....7 oz. per sq. yard

Flame Retardancy..... Cal. Fire Marshall, NFPA-701
CPAI-84, ASTEM-84 Class A
(ICC-ES REPORT ESR-2646) AC-167
Meets NFPA 90A /90B

Melt Temperature.....350 degrees F.

Tongue Tear.....Warp 43 lb.
Weft 48 lb. ASTM D2261-96

Air Permeability.....@ 125 Pa 0 cfm /sq. ft.

These are typical property values and are intended as guides only.

Phone 262-728-6860

Fax 262-728-6840