



Air Distribution Concepts 204 Hallberg Street Delavan, WI 53115 Ph: 262-728-6860 www.adctubes.com

Technical Data for Polyduct

Fire Retardant White

4.0 Mil

<u>Film Properties</u>	<u>ASTM Method</u>	<u>Units</u>	<u>Typical Value</u>
Melt Index	D-1238	g/10 Min.	1.3
Density	D-1505	g/cm	0.96
White	Loading	%	As Selected
Gloss	D-2457	%	40
Tensile Strength	D-882	PSI	
MD			3200
TD			2650
Ultimate Elongation	D-882	%	
MD			450
TD			800
Secant Modulus(1%)	D-882	PSI	
MD			27000
TD			31000
Yield @ 4.0 Mil		Sq. Inch/Lb	

NOTICE: All statements, information and data given herein are believed to be accurate and reliable. This data is presented without guaranty, warranty or responsibility of any kind, expressed or implied.

Statements or suggestions concerning possible use of our products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated, or that other measures may not be required.

The above typical values are intended as guides only and not as specification limits.