

POLYESTER

CONSTRUCTION	300 denier Coated Polyester With EPA approved antimicrobial agent
WEIGHT	. 7 oz. per sq. yard
FLAME RETARDANCY	CPAI-84, ASTME84, CLASS 1 ICCes Report (ESR-2646) AC-167 Meets NFPA 90A / 90B building materials Specs. For flame spread (25) and smoke development (50) CAN/ULC S-109
MELT TEMP	350 Degrees F
TONGUE TEAR	.Warp 43 lb. Weft 48 lb. ASTM D2261-96
AIR PERMEABILITY	.@ 125 Pa 0 cfm /sq. ft.

These are typical property values and are intended as guides only.

DISTRIBUTED BY:

3-21